

# MATI MOUNT TAPE

## WS-MATIMOUNT/25X25



Property	Value
Thickness	700µm
Release Liner	Differential siliconised kraft liner paper 100g/m <sup>2</sup>
Tensile Strength	88 N/25mm
Elongation at break	12%
Peel Strength: Open side (24 hrs)	65 N/25mm
Peel Strength: Closed side (20 mins)	60 N/25mm
Peel Strength: Closed side (24 hrs)	65 N/25mm
Initial Tack	(FINAT FTM 9 – Stainless Steel) 18 N/25mm
Initial Tack	(FINAT FTM 9 – Stainless Steel) 18 N/25mm 0.7 kN/m
Shear Strength (3kg static shear)	>800 hours
Service Temperature	5°C to 60°C
Shelf Life	2 years (+15°C to 25°C or +50°F to 77°F) And 50% relative humidity in dust free environment before use and in original packaging